

Selection & Specification Data

Generic Type	Polyamine Epoxy
Description	<u>Single-coat, plural-component applied, ultra-high build coating for use on steel and concrete substrates where rapid cure characteristics are required.</u> Phenoline 310 is applied by plural component spray equipment and offers the same high performance properties of Phenoline® 309, yet in a quick-curing formulation.
Features	<ul style="list-style-type: none"> ▪ Rapid cure-to-handle and cure-to-immersion characteristics. ▪ Low temperature (35°F) cure capabilities. ▪ Single coat application reduces labor costs. ▪ Ultra-high build capabilities provides a void-free film and excellent edge protection. ▪ Wide chemical resistance to acids, caustics and aliphatic solvents. ▪ Exceptional bond strength. ▪ Can be mat reinforced where exposure conditions dictate. ▪ VOC compliant to current AIM regulations
Color	White (0800), Gray (0700)
Finish	Eggshell
Primers	Self-priming
Dry Film Thickness	<u>1 coat system:</u> 20-25 mils (500-625 microns). <u>2 coat system:</u> 20-25 mils (500-625 microns) per coat.
Solids Content	By Volume: 98% ± 2%
Theoretical Coverage Rate	1572 mil ft ² (38.2 m ² /l at 25 microns) Allow for loss in mixing and application
VOC Values	As supplied: 0.1 lbs/gal (12 g/l) These are nominal values and may vary slightly with color.
Dry Temp. Resistance	Continuous: 140°F (60°C) Non-Continuous: 180°F (82°C) Discoloration and loss of gloss is observed above 140°F (60°C).
Wet Temp. Resistance	Immersion temperature resistance depends upon exposure. Consult Carboline Technical Service for specific information. It is recommended that metal tanks operating above 140°F (60°C) be insulated.
Limitations	<ul style="list-style-type: none"> ▪ Epoxies lose gloss, discolor and eventually chalk in sunlight exposure. ▪ This coating commonly develops an <i>amine-blush</i> during cure. While this condition will not adversely affect performance of the coating, this blush must be removed before applying additional coats and may require removal before placing into service.

Substrates & Surface Preparation

General	Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating.
Steel	<u>Immersion:</u> SSPC-SP5, 2-4 mils <u>Non-Immersion:</u> SSPC-SP10, 2-4 mils
Concrete	<u>Immersion and Non-Immersion:</u> Concrete must be cured 28 days at 75°F (24°C) and 50% relative humidity or equivalent. Prepare surfaces in accordance with ASTM D4258 Surface Cleaning of Concrete and ASTM D4259 Abrading Concrete. Voids in concrete may require surfacing.

Phenoline® 310

Application Equipment

Spray Application (Plural Component) Recommended for application by plural component airless spray. This is a high solids coating and may require adjustments in spray techniques. Wet film thickness is easily and quickly achieved. Contact Carboline Technical Service for plural component equipment recommendations.

Conventional Spray Not recommended

Airless Spray Not recommended

Brush Not recommended

Roller Not recommended

Mixing & Thinning

Mixing Power mix each component separately. Phenoline 310 is applied with two component airless spray.

Ratio 4:1 Ratio (A to B)

Thinning Not recommended. Use of thinners other than those supplied or recommended by Carboline may adversely affect product performance and void product warranty, whether expressed or implied.

Pot Life 25 minutes at 75°F (24°C). Pot life ends when material begins to thicken and starts to heat up. Pot life times will be less at higher temperatures.

Cleanup & Safety

Cleanup Use #2 Thinner or Acetone. In case of spillage, absorb and dispose of in accordance with local applicable regulations.

Safety Read and follow all caution statements on this product data sheet and on the MSDS for this product. Employ normal workmanlike safety precautions. Hypersensitive persons should wear protective clothing, gloves and use protective cream on face, hands and all exposed areas.

Ventilation Spray mist may cause explosion. When used as a tank lining or in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. In addition to ensuring proper ventilation, appropriate respirators must be used by all application personnel.

Caution This product contains flammable materials. Keep away from sparks and open flames. All electrical equipment and installations should be made and grounded in accordance with the National Electric Code. In areas where explosion hazards exist, workmen should be required to use non-ferrous tools and wear conductive and non-sparking shoes.

Application Conditions

Condition	Material	Surface	Ambient	Humidity
Normal	60°-85°F (16°-29°C)	60°-85°F (16°-29°C)	60°-90°F (16°-32°C)	0-80%
Minimum	35°F (2°C)	35°F (2°C)	35°F (2°C)	0%
Maximum	90°F (32°C)	125°F (52°C)	110°F (43°C)	90%

This product simply requires the substrate temperature to be above the dew point. Condensation due to substrate temperatures below the dew point can cause flash rusting on prepared steel and interfere with proper adhesion to the substrate. Special application techniques may be required above or below normal application conditions. To reduce outgassing when applying to concrete substrates, do not apply in direct sunlight or when surface temperatures are increasing. Best results are obtained when ambient and surface temperatures are decreasing or constant.

Curing Schedule

Surface Temp. & 50% Relative Humidity	Minimum Recoat Time	Maximum Recoat Time	Final Cure for Immersion Service
35°F (2°C)	16 Hours	36 Hours	36 Hours
60°F (16°C)	8 Hours	16 Hours	16 Hours
75°F (24°C)	4 Hours	8 Hours	8 Hours
90°F (32°C)	2 Hours	6 Hours	6 Hours

These times are based on a 20.0 mil (500 micron) dry film thickness. Higher film thickness, insufficient ventilation or cooler temperatures will require longer cure times. Condensation on the surface or humidity above 25% during application and curing will result in a surface haze or blush. Any haze or blush must be removed by water washing before recoating. During high humidity conditions, it is recommended that the application be done while temperatures are increasing. If the maximum recoat time is exceeded, the surface must be washed with detergent and water, then abraded by sweep blasting prior to the application of additional coats. For force curing, contact Carboline Technical Service for specific requirements.

Packaging, Handling & Storage

Shipping Weight (Approximate)	<u>1 Gallon Kit</u> 12 lbs. (5 kg)	<u>20 Gallon Kit</u> 165 lbs. (75 kg)
--------------------------------------	---------------------------------------	------------------------------------------

Flash Point (Setaflash) Part A: >205°F (96°C)
Part B: >205°F (96°C)

Storage (General) Store Indoors, out of direct sunlight.

Storage Temperature & Humidity 50°- 85°F (11°-30°C)
0-100% Relative Humidity

Shelf Life 1 year if stored at 50°-85°F. To ensure maximum film build, Phenoline 310 should be applied within three (3) months of the manufactured date.



350 Hanley Industrial Court St. Louis, MO 63144-1599
314-644-1000 314-644-4617 (fax) www.carboline.com

April 2000 replaces March 2000-2

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Carboline® and Phenoline® are registered trademarks of Carboline Company.